

**MatWeb, The Online Materials Database****Phosphor bronze 5% Sn, UNS C51000, H02 Temper wire****Subcategory:** Bronze; Copper Alloy; Metal; Nonferrous Metal**Key Words:** CDA 510, PB102, ISO CuSn5

<b>Component</b>	<b>Wt. %</b>
Cu	93.6 - 95.6
Fe	Max 0.1
P	0.03 - 0.35
Pb	Max 0.05
Sn	4.2 - 5.8
Zn	Max 0.3

**Material Notes:**

Good to excellent corrosion resistance. Excellent cold workability. Fabricated by blanking, drawing, bending, heading, and upsetting, shearing, roll threading, knurling and stamping.

**Applications:** bellows, bourdon tubing, clutch discs, cotter pins, diaphragms, fasteners, lock washers, wire brushes, chemical hardware, textile machinery, welding rod.

Trace content of Phosphorus.

Test specimen: wire - 2mm diameter.

<b>Physical Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Density	8.86 g/cc	0.32 lb/in <sup>3</sup>	at 20°C (68°F)

**Mechanical Properties**

Tensile Strength, Ultimate	585 MPa	84800 psi	
Tensile Strength, Yield	550 MPa	79800 psi	0.5% extension under load
Elongation at Break	8 %	8 %	In 50 mm

Modulus of Elasticity	110 GPa	16000 ksi	
Poisson's Ratio	0.341	0.341	
Machinability	20 %	20 %	UNS C36000 (free-cutting brass) = 100%
Shear Modulus	41 GPa	5950 ksi	

### Electrical Properties

---

Electrical Resistivity	8.7e-006 ohm-cm	8.7e-006 ohm-cm	at 20°C (68°F)
------------------------	-----------------	-----------------	----------------

### Thermal Properties

---

CTE, linear 250°C	17.8 $\mu\text{m}/\text{m}\cdot\text{°C}$	9.89 $\mu\text{in}/\text{in}\cdot\text{°F}$	from 20-300°C (68-570°F)
Specific Heat Capacity	0.38 J/g-°C	0.0908 BTU/lb-°F	
Thermal Conductivity	84 W/m-K	583 BTU-in/hr-ft <sup>2</sup> -°F	at 20°C (68°F)
Melting Point	975 - 1060 °C	1790 - 1940 °F	
Solidus	975 °C	1790 °F	
Liquidus	1060 °C	1940 °F	

### Processing Properties

---

Annealing Temperature	475 - 675 °C	887 - 1250 °F
-----------------------	--------------	---------------

Copyright 1996-2006 by Automation Creations, Inc. The information provided by MatWeb is intended for personal, non-commercial use. The contents, results, and technical data from this site may not be reproduced either electronically, photographically or substantively without permission from Automation Creations, Inc. No warranty, neither expressed nor implied, is given regarding the accuracy of this information. The user assumes all risk and liability in connection with the use of information from MatWeb.